



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : A61F 2/44	A1	(11) International Publication Number: WO 00/69374 (43) International Publication Date: 23 November 2000 (23.11.00)
(21) International Application Number: PCT/US00/05723 (22) International Filing Date: 3 March 2000 (03.03.00) (30) Priority Data: 09/311,431 13 May 1999 (13.05.99) US (71) Applicant: BOARD OF TRUSTEES OF THE UNIVERSITY OF ARKANSAS [US/US]; University of Arkansas, 2404 North University Avenue, Little Rock, AR 72207-3608 (US). (72) Inventor: EATON, L., Daniel; 14320 Jerome Drive, Little Rock, AR 72212 (US). (74) Agents: COX, Ray, F. et al.; Wright, Lindsey & Jennings, LLP, Suite 2200, 200 West Capitol, Little Rock, AR 72201-3699 (US).		(81) Designated States: AU, CA, JP, MX, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>With amended claims.</i>
(54) Title: ALLOPLASTIC VERTEBRAL DISK REPLACEMENT (57) Abstract <p>An alloplastic device and process for replacement of a damaged or diseased spinal vertebral column disk. The replacement disk (10) is hollow room temperature vulcanizable (RTV) silicone shaped to mimic the natural disk being replaced. The shape can be derived from a mold (20) of the natural disk or an MRI scan. The replacement disk (10) may be trabeculated and may be filled with a lubricating fluid (40) including triglyceride oil, preferably soybean oil. The replacement disk (10) is formed by allowing RTV silicone injected into a mold (20) to vulcanize until a wall (30) of sufficient thickness is formed. The unvulcanized silicone is expressed to form the hollow interior (31). The replacement disk (10) is formed with a nipple (13) having an interior concavity (32). The nipple (13) is cut from the body of the replacement disk (10) leaving an opening into the hollow interior. The nipple (13) is inverted and sealed into the opening so that the nipple (13) extends from the surface of the disk (10) into the interior (31) where it contacts the opposite wall (35) of the disk (10). The inverted nipple (13) thus provides a central support for the disk (10) and a valve means to inject the lubricating fluid (40) into the hollow interior (31). The concavity (32) of the inverted nipple (13) is filled with RTV silicone which vulcanizes and seals the opening. The hollow disk (10) lubricates itself since the lubricating fluid (40) percolates slowly through the silicone wall (30). Other uses include replacement for a worn out or injured meniscus, and other orthopedic applications including carpal tunnel damage or injuries.</p> <div data-bbox="788 970 1179 1164"> </div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Description

Alloplastic Vertebral Disk Replacement

5

Technical Field

The present invention relates to devices for the replacement of intervertebral disks damaged or destroyed by disease or trauma, and in particular, to a hollow prosthetic device and a method of forming a hollow
10 prosthetic device having a fluid infusion port which is sealed to prevent leakage.

Background Art

When intervertebral disks are damaged or destroyed by disease or
15 trauma, total removal of the disk is often indicated. Reconstruction or replacement of the function performed by the lost disk may require the use of autografts or allografts to fuse the adjacent vertebrae together. A more complete and natural restoration of function is possible with the implantation of prosthetic intervertebral disks.

20 U.S. Patent No. 5,514,180 discloses intervertebral prosthetic devices having fixed shapes for accommodating the defined surface contours of the vertebral endplates. The invention defines five morphological types of surfaces comprising a set of surfaces capable of accommodating the anatomy of most vertebral endplates. A method of digitizing the surface of a
25 vertebral body to determine a specific shape of a vertebral endplate is also disclosed. Furthermore this invention also relates to such prosthetic devices

incorporating osteoinductive material such as bone growth factors.

U.S. Patent No. discloses a method for replacing the nucleus pulposus of an intervertebral disk. The nucleus pulposus is removed and a flexible hollow prosthetic disk is inserted into the space defined by the annulus
5 fibrosis. The prosthetic disk is then filled with a gel material.

U.S. Patent No. 5,545,229 discloses an intervertebral disk spacer comprising a central core of soft elastomer approximating the size and shape of the nucleus pulposus, an outer ring of stiffer elastomeric material approximating the size and shape of the annulus fibrosis, and endplates of
10 stiff material incorporating a mechanism for attachment to the adjacent bony vertebral bodies.

U.S. Patent No. 4,863,477 discloses an intervertebral disk prosthesis molded in the shape of the natural disk. The replacement disk is molded of rubber or silicone rubber. The replacement disk is formed from two halves
15 joined together to form a hollow interior. After the disk is implanted between two vertebrae, a fluid, such as saline, is injected into the hollow interior space.

Various techniques are known for forming hollow prostheses. A technique developed by the inventor of the present invention is disclosed in
20 U.S. Patent Nos. 5,376,323; 5,855,606 and 5,700,288. The technique disclosed in these patents utilizes room temperature vulcanizable silicone. Room temperature vulcanizable silicone compositions are described generally in U.S. Patent Nos. 3,925,277 and 3,897,376. A technique for forming prosthetic devices having varying degrees of flexibility is disclosed in

U.S. Patent No. 4,735,754 to Buckner. This technique selectively removes silicone material from the device to form voids having the requisite degree of flexibility.

U.S. Patent No. 5,314,478 discloses a prosthesis that may be used as
5 a replacement for an intervertebral disk. The prosthesis is a composite of polyvinyl alcohol hydrogel and a ceramic or metallic porous body.

U.S. Patent No. 5,824,093 discloses a prosthetic spinal disk comprising a jacket surrounding a hydrogel core that is allowed to hydrate to a predetermined volume.

10 U.S. Patent No. 5,702,454 discloses a prosthetic implant for replacing a spinal disk. Support members are inserted into a cavity in the core of the intervertebral disk until the cavity is filled.

U.S. Patent No. 3,867,728 discloses a prosthesis for spinal repair comprising a core element having a flat top and bottom surfaces. The core is
15 made of elastic polymer and may be reinforced. A covering element secured to both flat surfaces provides a tissue ingrowth receptive material.

The limitations of the prior art are overcome by the present invention as described below.

20 *Disclosure of the Invention*

The present invention is an alloplastic device for replacement of a damaged, ruptured, disintegrated or diseased spinal vertebral column disk and a method of forming such a replacement disk. The replacement disk is hollow elastomer, preferably room temperature vulcanizable (RTV) silicone,

such as Silastic® medical adhesive silicone Type A (available from Dow Corning). The replacement disk is shaped to mimic the natural disk being replaced. The shape can be derived from a mold of the natural disk, if intact, or from a composite of fragments of the natural disk. If the natural disk is too
5 fragmented or altered by disease or trauma or otherwise does not present a good model for the development of a mold of the replacement device, an MRI scan can be used to develop the shape of the mold using known techniques such as computerized numerically controlled shaping machines.

The hollow elastomeric shape may be produced by the technique
10 disclosed in U.S. Patent No. 5,376,323, which is incorporated herein by reference. This technique allows various wall thicknesses to be formed depending on the load bearing requirements of the replacement disk. In addition, the replacement disk may be trabeculated or honeycombed with multiple chambers or multiple load bearing pillars. The hollow disk may be
15 filled with a triglyceride oil, such as soybean oil or rice oil, cerebrospinal fluid, seroma or synovial fluid, or a combination of any of these materials.

In the preferred embodiment the replacement disk is formed by allowing room temperature vulcanizable (RTV) silicone, such as Silastic®, injected into a mold to vulcanize at room temperatures until a wall of
20 sufficient thickness is formed. The unvulcanized RTV silicone is expressed to form the hollow interior. The replacement disk is formed with a nipple having an interior concavity. Once the replacement disk is removed from the mold and the unvulcanized RTV silicone expressed from the interior, the nipple is cut from the body of the replacement disk leaving an opening into

the hollow interior. The nipple is inverted and sealed into the opening so that the nipple extends from the surface of the replacement disk down into the interior where it contacts the opposite wall of the disk. The inverted nipple thus provides a central support for the disk. More importantly, the inverted
5 nipple provides an infusion port to inject a lubricating fluid, such as soybean oil, into the hollow interior of the disk. It should be understood that vulcanized RTV silicone is not self-sealing. Using the inverted nipple infusion port, however, the lubricating fluid is injected by a hypodermic needle into the sidewall of the infusion port. After the proper amount of fluid is injected, the
10 concavity of the infusion port is filled with RTV silicone, which then vulcanizes and seals the opening.

The disk is surgically positioned between two spinal vertebra to separate and provide a cushion against movement and compaction in the manner of a natural disk. The replacement disk also provides shock
15 absorption and maintains an appropriate and accurate distance between the vertebrae for safety, comfort and motility of the spinal column.

The hollow disk also lubricates itself since a triglyceride oil filling material, such as soybean oil in the preferred embodiment, percolates slowly through the silicone wall. A mixture of soybean oil and synovial fluid
20 continually lubricates the surfaces in the space between the vertebrae and the replacement disk. Genetic engineering of the structural formulas of soybean oil, seroma, and synovial fluid could be employed to optimize the molecular size of the fluids for the lubrication function.

The present invention provides definitive intervention for chronic physical problems, including pain. It is a solution for the problem of the ruptured disk and provides an alternative to vertebral fusion. The present invention may also allow correction of problems due to trauma. Although
5 described primarily as a vertebral disk replacement, the present invention is not so limited. Other uses include replacement for a worn out or injured miniscus, and other orthopedic applications including carpal tunnel damage or injuries.

It is therefore an object of the present invention to provide for a hollow
10 prosthesis formed with a nipple having an interior concavity for inversion and use as an infusion port to inject the filling material.

It is a further object of the present invention to provide for a filling material comprising a triglyceride oil, such as soybean oil or rice oil, for a hollow prosthesis in combination with a permeable wall for the hollow
15 prosthesis in order to allow the prosthesis to be self-lubricating.

These and other objects and advantages of the present invention will be apparent from a consideration of the following detailed description of the preferred embodiments in conjunction with the appended drawings as described following.

20

Brief Description of the Drawings

Fig. 1 is a perspective view of a mold for a replacement vertebral disk.

Fig. 2 is an exploded perspective view of the mold of Fig. 1 showing the shapes of the upper and lower halves of the mold and a molded

prosthesis in the lower half. The prosthesis is shown with a nipple molded into the prosthesis and the indentation in the upper half of the mold for producing the nipple.

Fig. 3 is a perspective view of the prosthesis removed from the mold
5 of Fig. 2

Figs. 4A-4D are sequence of elevational cross-sections of the prosthesis of Fig. 3. Fig. 4A shows the cross section of the prosthesis as it appears from the mold. Fig. 4B shows the nipple removed from the prosthesis, inverted and affixed into the interior of the prosthesis to form the
10 infusion port. Fig. 4C shows the prosthesis being filled with a filling material by hypodermic needle injected into the sidewall of the infusion port. Fig. 4D shows the interior concavity of the infusion port sealed to prevent leakage of the filling material.

Fig. 5 shows a perspective view of a sectioned prosthesis. In this
15 embodiment the interior of the prosthesis is honeycombed; i.e., divided into a plurality of chambers.

Fig. 6 shows a perspective view of a sectioned prosthesis. In this embodiment the interior is trabeculated; i.e., provided with a plurality of load bearing pillars.

20

Best Modes for Carrying Out the Invention

The present invention is an alloplastic device for replacement of a damaged, ruptured, disintegrated or diseased spinal vertebral column disk and a method of forming such a replacement disk. The replacement disk is a

hollow prosthesis formed from an elastomer, preferably a room temperature vulcanizable (RTV) silicone, such as Silastic® medical adhesive silicone Type A (available from Dow Corning).

With reference to Figs. 1-3, the replacement disk 10 is shaped to
5 mimic the natural disk being replaced. The shape can be derived from a mold of the natural disk, if intact, or from a composite of fragments of the natural disk. If the natural disk is too fragmented or altered by disease or trauma or otherwise does not present a good model for the development of a
10 mold of the replacement device, an MRI scan can be used to develop an image of the space occupied by the natural disk using known techniques such as computerized numerically controlled shaping machines. From the shape thus determined, a mold can be produced.

The mold 20 for producing the replacement disk 10 can be a two piece mold having an upper portion 21 and a lower portion 22. The hollow
15 elastomeric shape of the replacement disk 10 may be produced by the technique disclosed in U.S. Patent No. 5,376,323, which is incorporated herein by reference. This technique allows various wall thicknesses to be formed depending on the load bearing requirements of the replacement disk 10. For example, cervical disks may not require walls as thick as would be
20 appropriate for lumbar or sacral disks. If allowed to completely vulcanize, a solid disk may be formed for maximum load bearing capability. In addition, the replacement disk 10 may be trabeculated with multiple load bearing posts 11 as shown in Fig. 6 or honeycombed with multiple chambers 12 as shown in Fig. 5. In the later embodiments, the technique disclosed in U.S. Patent

No. 5,376,323 may not be appropriate and more complicated molding procedures may be required.

As may be seen from Figs. 2 and 3, the lower portion 22 of the mold 20 replicates the shape desired in the replacement disk 10 by replicating the shape of a natural disk. An additional feature not found in the natural disk is a nipple 13 formed on the replacement disk 10 by sculpting an indentation 14 in the upper portion 21 of the mold 20. The significance of the nipple 13 is discussed more fully below.

In the preferred embodiment the replacement disk 10 is formed by allowing room temperature vulcanizable (RTV) silicone, such as Silastic® medical adhesive silicone Type A, injected into the mold 20 to vulcanize at room temperatures until a wall 30 of sufficient thickness is formed as shown in Fig. 4A. The thickness of the wall 30 is determined by the load bearing requirements of the replacement disk 10. The unvulcanized RTV silicone within the replacement disk 10 is expressed to form the hollow interior 31. The replacement disk 10 is thus formed with the nipple 13 having an interior concavity 32.

Once the replacement disk 10 is removed from the mold 20 and the unvulcanized RTV silicone expressed from the interior 31, the nipple 13 is cut from the body 33 of the replacement disk leaving an opening in the upper surface 34 of the replacement disk 10 into the hollow interior 31. As shown in Fig. 4B, the nipple 13 is inverted and sealed into the opening on the upper surface 34 so that the nipple 13 extends from the upper surface 34 of the replacement disk 10 down into the interior 31 where it contacts the lower

surface 35 of the disk 10. The inverted nipple may be sealed to the lower surface 35 using silicone or the like. The inverted nipple 13 thus provides a central support for the disk 10. In other embodiments of the present invention the inverted nipple 13 need not actually contact or be bonded to the lower surface 35. If the disk 10 is to be formed as a solid disk, the nipple 13 may be removed and discarded.

The main function of the inverted nipple 13 is to provide an infusion port to inject a lubricating fluid, such as soybean oil or other triglyceride oil, or other filling material 40 into the hollow interior 31 of the disk. It should be understood that vulcanized RTV silicone is not self-sealing. Using the inverted nipple 13 as an infusion port, however, the filling material 40 is injected by a hypodermic needle 41 into a sidewall 50 of the inverted nipple 13. After the proper amount of filling material 40 is injected, the concavity 32 of the inverted nipple 13 is filled with RTV silicone which then vulcanizes and forms a plug 42 which seals the opening. It is thus possible to manufacture a seamless hollow prosthesis and to fill the hollow prosthesis even though the prosthesis is constructed of material that is not self-sealing.

The filling material 40 in the preferred embodiment is a triglyceride oil, such as soybean oil or rice oil. The filling material 40 may also be cerebrospinal fluid, seroma, synovial fluid, or a combination of these lubricating fluids. The preferred filling material 40 is soybean oil (trilipid Z5), which is a natural triglyceride and has been used for 40 years as an I.M. drug carrier. There is thus a long history of the safe application of soybean oil to human patients.

It has been determined that the hollow replacement disk 10 lubricates itself since soybean oil percolates slowly through the semi-permeable silicone wall 30. In the preferred embodiment, a mixture of soybean oil and synovial fluid continually lubricates the surfaces in the space between the vertebrae and the replacement disk 10. Genetic engineering of the structural formula of soybean oil, seroma, and synovial fluid could be employed to optimize the molecular size of the fluids for the lubrication function.

An experimental prototype of RTV silicone was vulcanized, filled with soybean oil and a soybean oil/seroma combination. The prototype was demonstrated to hold a vacuum and that the infusion port did not leak. The prototype also demonstrated percolation of the soybean oil and soybean oil/seroma combination through the semi-permeable wall of the prototype.

After the replacement disk 10 has been manufactured and the appropriate filling material injected into the replacement disk 10, the disk 10 is surgically positioned between two spinal vertebrae to separate and provide a cushion against movement and compaction in the manner of a natural disk. The replacement disk 10 also provides shock absorption and maintains an appropriate and accurate distance between the vertebrae for safety, comfort and motility of the spinal column.

20

Industrial Applicability

The present invention provides definitive intervention for chronic physical problems, including pain. It is a solution for the problem of the ruptured disk and provides an alternative to vertebral fusion. The present

invention may also allow correction of problems due to trauma. Although the present invention has been described with reference to an embodiment in which the prosthesis is a replacement for a vertebral disk, the invention is not so limited and would be applicable other prosthetic devices where self-

5 lubrication is desirable. Other uses include, without limitation, replacement for a worn out or injured miniscus, and other orthopedic applications including carpal tunnel damage or injuries.

The present invention has been described with reference to certain preferred and alternative embodiments that are intended to be exemplary

10 only and not limiting to the full scope of the present invention as set forth in the appended claims.

Claims

1. A hollow prosthesis, comprising:
at least one wall enclosing an interior space, said wall having an exterior surface and an interior surface;
5 an infusion port for injecting filling material into said interior of said hollow prosthesis;
said infusion port comprising a concavity on said exterior surface of said wall of said hollow prosthesis, said concavity being defined by an infusion wall extending from said exterior surface of said wall of said hollow
10 prosthesis into said interior of said hollow prosthesis whereby said filling material may be injected through said infusion wall into said interior.
2. The hollow prosthesis of claim 1 wherein said wall of said hollow prosthesis comprises room temperature vulcanizable silicone.
3. The hollow prosthesis of claim 2 further comprising a filling
15 material.
4. The hollow prosthesis of claim 3 wherein said filling material comprises a triglyceride oil.
5. The hollow prosthesis of claim 4 wherein said triglyceride oil comprises soybean oil
- 20 6. The hollow prosthesis of claim 5 wherein said wall of said hollow prosthesis comprises inferior and superior walls shaped to conform to vertebral endplates and a lateral wall shaped to conform to an intervertebral disk space.

7. The hollow prosthesis of claim 6 wherein said infusion port is affixed to said inferior wall and to said superior wall.

8. The hollow prosthesis of claim 7 further comprising a plurality of chambers dividing said interior.

5 9. The hollow prosthesis of claim 7 further comprising a plurality of interior pillars, each of said pillars being affixed to said inferior wall and to said superior wall.

10. A method of forming a hollow prosthesis, comprising the steps of:

10 (a) forming a mold having the shape of the desired prosthesis, said mold further having a depression for forming a nipple on the surface of the prosthesis;

(b) injecting said mold with room temperature vulcanizable silicone;

(c) allowing sufficient time for walls of vulcanized silicone to form
15 on the interior surfaces of the mold to a desired thickness so that the nipple retains an interior concavity;

(d) removing the prosthesis from the mold and expressing
unvulcanized silicone from the interior of the prosthesis; and

(e) excising the nipple from the prosthesis, inverting the nipple into
20 the opening thus created into the hollow interior of the prosthesis, and sealing the nipple into the wall of the prosthesis.

11. The method of claim 10 further comprising the steps of injecting filling material into the interior of the prosthesis through the concavity of the inverted nipple and sealing the concavity with room temperature vulcanizable

silicone.

12. The method of claim 11 wherein said filling material comprises a triglyceride oil.

13. The method of claim 12 wherein said triglyceride oil comprises
5 soybean oil

14. The method of claim 13 wherein said prosthesis is molded into the shape of an intervertebral disk.

15. The method of claim 14 wherein step (a) comprises taking an impression of a natural intervertebral disk and forming the mold from the
10 impression of the natural intervertebral disk.

16. The method of claim 14 wherein step (a) comprises scanning an intervertebral disk space, forming an impression of the intervertebral disk space by computerized numerically controlled shaping, and forming the mold from the impression.

15

AMENDED CLAIMS

[received by the International Bureau on 11.July.2000.(11.07.00);
original claims 1 – 6 cancelled; original claim 7 amended; new claims 17 and 18 added;
other claims unchanged (3 pages)]

7. A hollow prosthesis, comprising:

at least one wall enclosing an interior space, said at least one wall
having an exterior surface and an interior surface;

5 a filling material comprising a triglyceride oil;

an infusion port for injecting said filling material into said interior of
said hollow prosthesis;

said infusion port comprising a concavity on said exterior surface of
said at least one wall of said hollow prosthesis, said concavity being defined
10 by an infusion wall extending from said exterior surface of said at least one
wall of said hollow prosthesis into said interior of said hollow prosthesis
whereby said filling material may be injected through said infusion wall into
said interior;

wherein said at least one wall of said hollow prosthesis comprises
15 room temperature vulcanizable silicone; and

wherein said at least one wall of said hollow prosthesis comprises
inferior and superior walls shaped to conform to vertebral endplates and a
lateral wall shaped to conform to an intervertebral disk space; and

wherein said infusion port is affixed to said inferior wall and to said
20 superior wall.

8. The hollow prosthesis of claim 7 further comprising a plurality of
chambers dividing said interior.

9. The hollow prosthesis of claim 7 further comprising a plurality of
interior pillars, each of said pillars being affixed to said inferior wall and to

said superior wall.

10. A method of forming a hollow prosthesis, comprising the steps of:

(a) forming a mold having the shape of the desired prosthesis, said
5 mold further having a depression for forming a nipple on the surface of the prosthesis;

(b) injecting said mold with room temperature vulcanizable silicone;

(c) allowing sufficient time for walls of vulcanized silicone to form
on the interior surfaces of the mold to a desired thickness so that the nipple
10 retains an interior concavity;

(d) removing the prosthesis from the mold and expressing
unvulcanized silicone from the interior of the prosthesis; and

(e) excising the nipple from the prosthesis, inverting the nipple into
the opening thus created into the hollow interior of the prosthesis, and
15 sealing the nipple into the wall of the prosthesis.

11. The method of claim 10 further comprising the steps of injecting filling
material into the interior of the prosthesis through the concavity of the
inverted nipple and sealing the concavity with room temperature vulcanizable
silicone.

20 12. The method of claim 11 wherein said filling material comprises
a triglyceride oil.

13. The method of claim 12 wherein said triglyceride oil comprises
soybean oil

14. The method of claim 13 wherein said prosthesis is molded into

the shape of an intervertebral disk.

15. The method of claim 14 wherein step (a) comprises taking an impression of a natural intervertebral disk and forming the mold from the impression of the natural intervertebral disk.

5 16. The method of claim 14 wherein step (a) comprises scanning an intervertebral disk space, forming an impression of the intervertebral disk space by computerized numerically controlled shaping, and forming the mold from the impression.

10 17. The hollow prosthesis of claim 8 wherein said triglyceride oil is soybean oil.

18. The hollow prosthesis of claim 9 wherein said triglyceride oil is soybean oil.

1/3

FIG 2





FIG 1



2/3

FIG. 3




FIG. 4A




FIG. 4B




FIG. 4C





FIG. 4D



3/3

FIG. 6





FIG. 5



INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/05723

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61F 2/44

US CL : 264/222; 623/12, 17

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 264/222; 623/12, 16, 17, 901

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EAST

Search Terms: (prosthesis, form or construct or made or make or manufacture, mold, vulcanized adj silicone)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ----- Y	US 4,643,733 A (BECKER) 17 February 1987, Fig. 7, and col. 4 lines 10-12.	1 ----- 1-6
Y	US 5,496,367 A (FISHER) 05 March 1996, col. 2 lines 41-45.	4-6
Y	US 5,123,926 A (PISHARODI) 23 June 1992, Fig. 4, col. 3 lines 19-23.	1-3, 5, 6
A	US 4,944,749 A (BECKER) 31 July 1990, whole document.	1-16
A	US 5,156,777 A (KAYE) 20 October 1992, whole document.	1-16

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* Inter document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*G* document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means	
P document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

30 MAY 2000

Date of mailing of the international search report

20 JUN 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

EDUARDO C. ROBERT

Telephone No. (703) 305-7333

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/05723

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,504,300 A (DEVANATHAN et al.) 02 April 1996, whole document.	1-16
A	US 5,558,829 A (PETRICK) 24 September 1996, whole document.	1-16